

- PVOH Standard -

Product from Germany;

	Grade	Viscosity ¹⁾ [mPa × s]	Hydrolysis [mol.-%]	Ash Max ²⁾ [%]	Volatile Max ³⁾ [%]
Partially Hydrolysed	Mowiol 3-85	3.4 - 4.0	84.2 - 86.2	0.5	5.0
	Mowiol 4-88	3.5 - 4.5	86.7 - 88.7	0.5	5.0
	Mowiol 5-88	5.0 - 6.0	86.7 - 88.7	0.5	5.0
	Mowiol 8-88	7.0 - 9.0	86.7 - 88.7	0.5	5.0
	Mowiol 13-88	11.5 - 14.5	86.7 - 88.7	0.5	5.0
	Mowiol 18-88	16.5 - 19.5	86.7 - 88.7	0.5	5.0
	Mowiol 23-88	21.5 - 24.5	86.7 - 88.7	0.5	5.0
	Mowiol 26-88	24.5 - 27.5	86.7 - 88.7	0.5	5.0
	Mowiol 32-88	30.0 - 34.0	86.7 - 88.7	0.5	5.0
	Mowiol 40-88	38.0 - 42.0	86.7 - 88.7	0.5	5.0
	Mowiol 47-88	45.0 - 49.0	86.7 - 88.7	0.5	5.0
	Mowiol 56-88	52.0 - 60.0	86.7 - 88.7	0.5	5.0
	Mowiol 30-92	28.0 - 32.0	91.5 - 93.3	0.5	5.0
Fully Hydrolysed	Mowiol 4-98	4.0 - 5.0	98.0 - 98.8	0.5	5.0
	Mowiol 6-98	5.0 - 7.0	98.0 - 98.8	0.5	5.0
	Mowiol 10-98	9.0 - 11.0	98.0 - 98.8	0.5	5.0
	Mowiol 20-98	18.5 - 21.5	98.0 - 98.8	0.5	5.0
	Mowiol 30-98	28.5 - 31.5	98.0 - 98.8	0.5	5.0
	Mowiol 56-98	52.0 - 60.0	98.0 - 98.8	1.0	5.0
	Mowiol 15-99	12.5 - 17.5	99.0 - 99.8	0.5	5.0
Mowiol 28-99	26.0 - 30.0	99.0 - 99.8	0.5	5.0	

1) of a 4 % aqueous solution at 20 °C determined by Hoppler viscometer (DIN 53015).

2) calculated as Na₂O

3) after 3 hours drying at 105 °C (DIN 53189). Methanol content: less than 3 %.

This information is based on our present state of knowledge and is intended to provide general notes on our products on their use. It should therefore not be constructed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Condition of Sale.

- PVOH Standard -

Product from Singapore;

	Grade	Viscosity ¹⁾ [mPa x s]	Hydrolysis [mol.-%]	Ash Max ²⁾ [%]	Volatile Max ³⁾ [%]
Partially	PVA 205	4.6 - 5.4	86.5 - 89.0	0.4	5.0
Hydrolysed	PVA 205MB ⁴⁾	4.6 - 5.4	86.5 - 89.0	0.4	5.0
	PVA 217	20.5 - 24.5	87.0 - 89.0	0.4	5.0
	PVA 217SB ⁴⁾	20.5 - 24.5	87.0 - 89.0	0.4	5.0
	PVA 217MB ⁴⁾	20.5 - 24.5	87.0 - 89.0	0.4	5.0
	PVA 220	27.0 - 33.0	87.0 - 89.0	0.4	5.0
	PVA 220SB ⁴⁾	27.0 - 33.0	87.0 - 89.0	0.4	5.0
	PVA 224	40.0 - 48.0	87.0 - 89.0	0.4	5.0
	PVA 224SB ⁴⁾	40.0 - 48.0	87.0 - 89.0	0.4	5.0
	PVA 225	45.0 - 52.0	86.5 - 89.0	0.4	5.0
Medium	PVA CST	24.0 - 30.0	95.5 - 96.5	0.4	5.0
Hydrolysed					
Fully	PVA 105	5.2 - 6.0	98.0 - 99.0	0.7	5.0
Hydrolysed	PVA 117	25.0 - 30.0	98.0 - 99.0	0.4	5.0

1) of a 4 % aqueous solution at 20 °C, determined by Brookfield viscometer (JIS K6726)

2) calculated as Na₂O

3) after 3 hours drying at 105 °C (JIS K6726). Methanol content: less than 3 %.

4) MB, SB: anti-foaming/defoaming grade; S: finer powder grade

This information is based on our present state of knowledge and is intended to provide general notes on our products on their use. It should therefore not be constructed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Condition of Sale.

- PVOH Standard plus -

	Grade	Viscosity ¹⁾ [mPa × s]	Hydrolysis [mol.-%]	Ash Max ²⁾ [%]	Volatile Max ³⁾ [%]
Fine powder	Mowiol 3-85 G4	3.0 - 4.0	84.2 - 86.2	0.5	5.0
	Mowiol 4-88 G2	3.5 - 4.5	86.7 - 88.7	0.5	5.0
	Mowiol 8-88 G2	7.0 - 9.0	86.7 - 88.7	0.5	5.0
	Mowiol 18-88 G2	16.5 - 19.5	86.7 - 88.7	0.5	5.0
	Mowiol 23-88 G2	21.5 - 24.5	86.7 - 88.7	0.5	5.0
	Mowiol 47-88 G2	45.0 - 49.0	86.7 - 88.7	0.5	5.0
	Mowiol 56-98 G2	52.0 - 60.0	98.0 - 98.8	0.5	5.0
Low ash	Mowiol 4-88 low ash	3.5 - 4.5	86.7 - 88.7	0.09	5.0
	Mowiol 8-88 low ash	7.0 - 9.0	86.7 - 88.7	0.09	5.0
	Mowiol 40-88 low ash	38.0 - 42.0	86.7 - 88.7	0.09	5.0
	Mowiol 4-98 low ash	4.0 - 5.0	98.0 - 98.8	0.09	5.0
	Mowiol 56-98 low ash	52.0 - 60.0	98.0 - 98.8	0.09	5.0
	Mowiol 28-99 low ash	26.0 - 30.0	99.0 - 99.8	0.09	5.0

1) of a 4 % aqueous solution at 20 °C determined by Hoppler viscometer (DIN 53015).

2) calculated as Na₂O

3) after 3 hours drying at 105 °C (DIN 53189). Methanol content: less than 3 %.

4) Particle size is below 200 μm.

This information is based on our present state of knowledge and is intended to provide general notes on our products on their use. It should therefore not be constructed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Condition of Sale.

- PVOH Specialties-

	Grade	Viscosity ¹⁾ [mPa × s]	Hydrolysis [mol.-%]	Ash Max ²⁾ [%]	Volatile Max ³⁾ [%]
High MW	PVA 236	90 - 110	87.0 - 89.0	0.4	5.0
Low Hydrolyzed	PVA 420H	29.0 - 35.0	79.0 - 81.0	0.4	5.0
	PVA 420	37.0 - 45.0	79.0 - 81.0	0.4	5.0
	PVA 424H	45.0 - 51.0	78.5 - 80.5	0.2	5.0
	PVA 403	2.8 - 3.3	78.5 - 81.5	0.4	5.0
	PVA 405	4.5 - 5.2	80.0 - 83.0	0.4	5.0
	PVA 505	4.2 - 5.0	72.5 - 74.5	0.4	5.0
Water	PVA LM-20	3.0 - 4.0 ⁴⁾	38.0 - 42.0	n.a.	5.0
Dispersible	PVA LM-10HD	4.5 - 5.7 ⁴⁾	38.0 - 42.0	n.a.	5.0

1) of a 4 % aqueous solution at 20 °C, determined by Brookfield viscometer (JIS K6726)

2) calculated as Na₂O

3) after 3 hours drying at 105 °C (JIS K6726). Methanol content: less than 3 %.

4) solvent; water / methanol = 1/1

	Grade	Viscosity ¹⁾ [mPa × s]	Hydrolysis [mol.-%]	Ash Max ²⁾ [%]	Volatile Max ³⁾ [%]
Carboxylic acid	KL-118	29.0 - 34.0	95.0 - 99.0	n.a.	n.a.
	KL-318	20.0 - 30.0	85.0 - 90.0	n.a.	5.0
	KL-506	5.2 - 6.2	74.0 - 80.0	n.a.	5.0
	OTP-5	6.0 - 7.0	85.0 - 90.0	n.a.	5.0
	SD-1000	2.3 - 3.4	83.0 - 88.0	n.a.	5.0
Cationic group	CM-318	17.0 - 27.0	86.0 - 91.0	n.a.	n.a.
	C-506	4.0 - 6.0	74.0 - 80.0	n.a.	n.a.
Silanol	R- 1130	20.0 - 30.0	98.0 - 99.0	n.a.	5.0
	R- 2105	4.5 - 6.0	98.0 - 99.0	n.a.	n.a.

1) of a 4 % aqueous solution at 20 °C, determined by Brookfield viscometer (JIS K6726)

2) calculated as Na₂O

3) after 3 hours drying at 105 °C (JIS K6726). Methanol content: less than 3 %.

This information is based on our present state of knowledge and is intended to provide general notes on our products on their use. It should therefore not be constructed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Condition of Sale.

EXCEVAL™

	Grade	Viscosity ¹⁾ [mPa × s]	Hydrolysis [mol.-%]	Ash Max ²⁾ [%]	Volatile Max ³⁾ [%]
Super Hydrolyzed	HR-3010	12.0 - 16.0	99.0 - 99.4	0.4	5.0
Fully Hydrolyzed	RS-2117	23.0 - 30.0	97.5 - 99.0	0.4	5.0
	AQ-4104	3.5 - 4.5	98.0 - 99.0	0.4	5.0
Medium Hydrolyzed	RS-1717	23.0 - 30.0	92.0 - 94.0	0.4	5.0
	RS-2817SB	23.0 - 30.0	95.5 - 97.5	0.4	5.0

1) of a 4 % aqueous solution at 20 °C, determined by Brookfield viscometer (JIS K6726)

2) calculated as Na₂O

3) after 3 hours drying at 105 °C (JIS K6726). Methanol content: less than 3 %.

Thermoplastic PVOH;

	Grade	Melt Flow Rate 2.16 kg [g/10min.]	MP [°C]	Tg [°C]	Solubility
Mowiflex	TC 232	< 1 (39; 21.6kg)	190	178	34 Room temperature
CP-polymer	CP - 1220 T10	8 - 12	190	170	40 Room temperature
	CP - 1210 T30	1.5 - 3.5	190	170	50 Room temperature
	CP - 4104 MI	70 - 90	230	210	55 Hot water

This information is based on our present state of knowledge and is intended to provide general notes on our products on their use. It should therefore not be constructed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Condition of Sale.